

PP-R - TUBES

MATERIAL

PP-R (polypropilene-random). This material is appropriate to be used in contact with drinkable water and other fluids at temperatures which can go until 110°C. This material is in accordance with the standards ISO/TR7471.

STANDARDS

The PLIMAT tubes in PP-R to weld strictly respect the standard DIN 8077 and 8078.

ASSEMBLY

By welding using an appropriate socket fusion machine. The tubes in PP-R are expected to be assembled with other fittings in plastic material (PP-R).

SERVICE PRESSURE

The service pressure, just as an indication, is of 20 bar at 20°C (water) or 4 bar at 90°C (water).

ABBREVIATION INTERPRETATION

- d - Nominal diameter of the welding parts
- Gr - Approximate weight of fittings in grams
- ★ - Products not manufactured by Plimat, S.A.

Note: each road of tube has 5 meters of length